



Report of Threaded Rod Shear Test

Client: Bonstone Material Corporation **Report No.:** 902317
Project No.: 0611892 **Date of Service:** June 30, 2006

Stone Type: Cold Spring Granite
Adhesive: Bonstone Clear Gel Epoxy

Test Method: ASTM C 1354, Standard Test Method for Strength of Individual Stone
 Anchorages in Dimension Stone

Calculation: Anchorage system load = Test machine load

Loading: Constant rate of loading at 600 lbs./minute until failure

Anchor Description: 1/4" diameter threaded rod with nominal 1" embedment

Nominal Dimensions:

Length (inches)	Width (inches)	Thickness (inches)
12	12	2.00

Conditioning: Tested in an "as is" condition

Finish: Honed

Sample Number	Failure Mode	Anchorage System Load (lbf.)
1	Bolt sheared	2,743
2	Bolt sheared	2,618
3	Bolt sheared	2,783
4	Bolt sheared	2,791
5	Bolt sheared	2,976
Average Anchorage System Load:		2,782
Standard Deviation:		129
Variance (percent):		4.64